

Razeen® LR 1110

Unmodified liquid Epoxy Resin



General Razeen® LR 1110 is an unmodified liquid epoxy resin similar to Razeen® LR 1100 but with slightly lower viscosity and higher purity.

Applications Due to its extremely low hydrolyzable chlorine (max 200 ppm) content Razeen® LR 1110 is also a special resin for electrodeposition (cataphoritic) primers mainly used in the automotive industry.

Properties

- Medium viscosity and high reactivity
- Compatible with various hardeners, reactive diluents and accelerators
- Low hydrolysable chlorine content and therefore slight tendency to cristalization at low temperature.
- Confirms to FDA listing

The resins formulated yeild:

- Superior mechanical and electrical properties
- Execlent chemical and water resistance

Specific Key Data	Property	Value	Test method
	Appearance	Clear, no contamination	JCTM 001
	Color APHA	125 max.	ASTM D-1209
	Epoxy value	5.32 - 5.49 eq/Kg	ASTM D-1652
	Weight per epoxide	182 - 188 g/eq	ASTM D-1652
	Viscosity @ 25°C (77°F)	10,000 - 12,000 mPa.s	ISO 12058-1
	Hydrolyzable Chlorine	200 ppm max.	JCTM 195
	Water Content (KF)	0.08% max.	ASTM D-4017

Specific key data are individually checked throughout, guaranteed and included in certificate of analysis.

Typical Key Data	Property	Value	Test method
	Residual Epichlorohydrin	10.0 ppm max.	JCTM GC6010
	Density at 25°C	1.16 g/cm ³	ISO 1675
	Flash point, closed up	≥ 200 °C	ISO 2719

Typical key data are spot checked; the values are typical for the product and are indicated for information only. The values are not included in certificate of analysis.

As-supplied form	Liquid
Odor	None
Shelf life (at storage temperature between 10-50°C) (See expiry date on original container)	4 years
Hazardous decomposition products (When disposed of in fire)	Carbon monoxide, carbon dioxide and other toxic gases and vapors.
Disposal	Regular procedures approved

Packaging and Storage Razeen® LR 1110 is supplied in bulk and in 240 kg. steel drums. This product has a minimum shelf life of four years when stored in unopened sealed containers in a dry location at room temperature. Like most liquid epoxy resins, Razeen® LR 1110 may crystallize when stored below room temperature. Heating the resin to 60-70°C (140-160°F), for several hours will re-liquefy it and restore its original properties.

Handling/Safety Precautions **Warning: Causes irritation.
May cause allergic skin reaction.**
Avoid contact with eyes, skin or clothing.
Avoid breathing vapor, mist or spray.
Use with adequate ventilation.
Promptly remove wet, contaminated clothing and wash before reuse.
Wash after handling.
Store in a cool, dry area in closed containers.

Please read Material Safety Data Sheet before using.

Note Razeen® is a registered trademark of JANA or an affiliate thereof.

Jubail Chemical Industries Co. (JANA)
P.O Box 10661
Jubail Industrial city 31961
Kingdom of Saudi Arabia
Tel : +966 3 3585002
Fax : +966 3 3585113
Website : www.jana-ksa.net

ISO 9001 : 2000



0010737-1044329

DISCLAIMER:

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED UPON OUR DATA BELIEVED TO BE CORRECT. HOWEVER, SINCE THE CONDITION OF USE ARE BEYOND OUR CONTROL, NO GUARANTEE OR WARRANTY OF ANY KIND OF EXPRESSED OR IMPLIED IS MADE WITH RESPECT TO THE INFORMATION CONTAINED HEREIN.